

Test Report No.: 10255 / 35018

Date: 19.09.2012

BASF SE
Brandschutztechnik
G-KTF/EA - A521
D-67056 Ludwigshafen

Test according to

DIN 5510 Part 2 : 2009-05

Preventive fire protection in railway vehicles - Part 2: Fire behaviour and fire side effects of materials and parts; Classification, requirements and test methods Test according to DIN 54837 : 2007-12 Testing of materials, small components and component sections for rail vehicles - Determination of burning behaviour using a gas burner

Client:

Henkel AG & Co. KGaA Heidelberg
Standort Heidelberg
Henkel-Teroson-Strasse 57

69123 Heidelberg

The results refer exclusively to the tested samples.

As an accredited Test Laboratory, the BASF SE Fire Safety Technology Test Centre is authorized to conduct fire tests in accordance with DIN EN ISO/IEC 17025 : 2005.

DAkKS-Register-No.: D-PL-14121-07-00



ID number EBA (German Rail): EBA – 012 / 07 / 10 –

BASF – Fire Safety Technology

Test according to DIN 5510 Part 2 : 2009-05
Preventive fire protection in railway vehicles - Part 2: Fire behaviour and fire side effects of materials and parts; Classification, requirements and test methods
Test according to DIN 54837 : 2007-12 Testing of materials, small components and component sections for rail vehicles - Determination of burning behaviour using a gas burner

Test Report No.: 10255 / 35018

Receipt of order: 07.09.2012
Receipt of samples: 07.09.2012
Date of test: 20.09.2012

1. Material: (Information supplied by client)

Terophon 123

Colour:

Field of application: Sound-deadening coating

2. Summary of results and classification:

Length of damaged area	8,0 cm	Combustibility	S4
Afterflame time	0 s		
Integral of smoke development	0 %•min	Smoke development class	SR2
Falling debris	no droplets / debris	Dripping class	ST2


Remarks:

Note: This report is valid for 3 years according to DIN 5510-2 (2009:05), if not differently regulated by the responsible authority.

Any conclusions we draw about the fire safety of the materials we test are based exclusively on the results of the test under the conditions described.

The extent to which such conclusions can be applied to non-tested material under non-standard conditions is the sole responsibility of the customer and is done so at his own risk.

BASF Fire Safety Technology


Dr. Henn
Head of Laboratory

Ludwigshafen, 20.09.2012


Spielmann
Technician

BASF – Fire Safety Technology

Test according to DIN 5510 Part 2 : 2009-05
Preventive fire protection in railway vehicles - Part 2: Fire behaviour and fire side effects of materials and parts; Classification, requirements and test methods
Test according to DIN 54837 : 2007-12 Testing of materials, small components and component sections for rail vehicles - Determination of burning behaviour using a gas burner

Test Report No.: 10255 / 35018

3. Material:

Information supplied by client

Terophon 123
dry layer thickness: ca. 2,5 - 3,0mm

Additional details from test laboratory

Sound-deadening coating on aluminum sheet (d=1mm).
Colour: beige.

4. Samples:

Sample size (determined by BASF test laboratory):

Length:	500,00 [mm]	Weight:	492,00 [g]
Width:	190,00 [mm]	Weight per unit area:	5,17 [kg/m ²]
Thickness:	3,40 [mm]	Density:	[kg/m ³]
Outer diameter:	[mm]	Remarks:	
Inner Diameter:	[mm]	thickness fluctuations:	3,0mm - 3,8mm

Pre-conditioning:

	Conditions	Duration days
Client: (Information supplied by client)	Normal 23/50-1 DIN 50014	
Test Laboratory:	Standard 23/50-1 DIN 50014	13

Sample preparation:

Exposed surface: coated surface

BASF – Fire Safety Technology

Test according to DIN 5510 Part 2 : 2009-05
Preventive fire protection in railway vehicles - Part 2: Fire behaviour and fire side effects of materials and parts; Classification, requirements and test methods
Test according to DIN 54837 : 2007-12 Testing of materials, small components and component sections for rail vehicles - Determination of burning behaviour using a gas burner

Test Report No.: 10255 / 35018

5. Test results:

Test apparatus: DIN 50 050	Sample:	1	2	3	4	5	Avg.
Ignition	at [min:s]	0:40	0:40	0:41	0:45	0:40	0:41
	Afterflame time [s]	0	0	0	0	0	0
Glowing	at [min:s]	1:20	1:22	1:20	1:25	1:30	1:23
	Afterglow time [s]	0	0	0	0	0	0
Flame height	Maximum [cm]	8	8	8	8	8	8
	at [min:s]	1:00	1:00	1:00	1:00	1:00	1:00
Falling debris	at [min:s]	---	---	---	---	---	
	Burning duration [s]	---	---	---	---	---	---
Smoke density	Maximum (%)	0	0	0	0	0	0
	at [min:s]	---	---	---	---	---	
Integral of smoke development	[% *min]	0	0	0	0	0	0
Max. length of damaged area	[cm]	8	9	8	8	8	8,2
Termination by extinguishing at	[min:s]	---	---	---	---	---	
Burning or melting through the sample	[yes/no]	no	no	no	no	no	

Observations:

6. Test equipment:

Test apparatus	PK 0011
Sliding gauge	MB 0036
Balance	MW 0003
Light measurement system	ML 0003
Data acquisition	MC 0007
Burner nozzle	BN 0002
Mass flow meter	MG 0045

Test according to DIN 5510 Part 2 : 2009-05
Preventive fire protection in railway vehicles - Part 2: Fire behaviour and fire side effects of materials and parts; Classification, requirements and test methods
Test according to DIN 54837 : 2007-12 Testing of materials, small components and component sections for rail vehicles - Determination of burning behaviour using a gas burner

Test Report No.: 10255 / 35018

7. Requirements:

Standard	Criteria	Classification
DIN 5510 Part 2	Combustibility class	
	Length of damaged area: ≤ 30 cm Afterflame time: Burning to the end of test and extinguishing allowed	S2
	Length of damaged area: ≤ 25 cm Afterflame time: ≤ 100 s (no single value ≥ 120 s)	S3
	Length of damaged area: ≤ 20 cm Afterflame time: ≤ 10 s	S4
	Length of damaged area: 0 cm Afterflame time: 0 s	S5
	Smoke development class	
	Integral of smoke development: > 100 %•min	SR1 not achieved
	Integral of smoke development: ≤ 100 %•min	SR1
	Integral of smoke development: ≤ 50 %•min	SR2
	Dripping class	
	Burning droplets / debris	ST1
	No burning droplets / debris *	ST2

* A classification as ST2 can also be achieved in case of burning droplets/debris, provided that the average time of afterburning is ≤ 20 seconds

BASF – Fire Safety Technology

Test according to DIN 5510 Part 2 : 2009-05
Preventive fire protection in railway vehicles - Part 2: Fire behaviour and fire side effects of materials and parts; Classification, requirements and test methods
Test according to DIN 54837 : 2007-12 Testing of materials, small components and component sections for rail vehicles - Determination of burning behaviour using a gas burner

Test Report No.: 10255 / 35018

8. Pictures:

