

Test Report No.: 10621 / 36371

Date: 16.05.2013

BASF SE
Brandschutztechnik
G-PMF/EA - A521
D-67056 Ludwigshafen

Test according to

DIN 5510 Part 2 : 2009-05

Preventive fire protection in railway vehicles - Part 2: Fire behaviour and fire side effects of materials and parts; Classification, requirements and test methods Determination of smoke toxicity in the smoke chamber according to ISO 5659-2

Client:

Henkel AG & Co. KGaA Heidelberg
Standort Heidelberg
Henkel-Teroson-Strasse 57

69123 Heidelberg

The results refer exclusively to the tested samples.

As an accredited Test Laboratory, the BASF SE Fire Safety Technology Test Centre is authorized to conduct fire tests in accordance with DIN EN ISO/IEC 17025 : 2005.

DAkkS-Register-No.: D-PL-14121-07-00



ID number EBA (German Rail): EBA – 012 / 07 / 10 –

BASF – Fire Safety Technology

Test according to DIN 5510 Part 2 : 2009-05
Preventive fire protection in railway vehicles - Part 2: Fire behaviour and fire side effects of materials and parts; Classification, requirements and test methods
Determination of smoke toxicity in the smoke chamber according to ISO 5659-2

Test Report No.: 10621 / 36371

Receipt of order: 11.04.2013
Receipt of samples: 03.05.2013
Date of test: 16.05.2013

1. **Material:** (information supplied by client)

Terotex 218

Colour:

Field of application: Sound deadening / underbody protection

2. **Summary of results and classification:**

Fractional effective dose		Requirement set No. Hazard Level	Allowable time of exposure	DIN 5510-2
FED ₁₅	0,08	*	30 min	FED ≤ 1 fulfilled
FED ₃₀	0,18	*		


Remarks:

*) no requirements defined.


Note: This report is valid for 3 years according to DIN 5510-2 (2009:05), if not differently regulated by the responsible authority.

**Any conclusions we draw about the fire safety of the materials we test are based exclusively on the results of the test under the conditions described.
The extent to which such conclusions can be applied to non-tested material under non-standard conditions is the sole responsibility of the customer and is done so at his own risk.**

BASF Fire Safety Technology


Dr. Henn
Head of Laboratory

Ludwigshafen, 16.05.2013


Spielmann
Technician

Test Report No.: 10621 / 36371

3. Material:

Information supplied by client:

Terotex 218

Composition: product applied on aluminium sheet, layer thickness of dried product appr. 2.5 - 3mm

Additional details from test laboratory

Colour coated side: grey

Aluminium sheet thickness: 1.00mm

4. Samples:

Sample size (determined by BASF test laboratory):

Length:	75,20 [mm]	Weight:	33,90 [g]
Width:	74,90 [mm]	Weight per unit area:	6,01 [kg/m ²]
Thickness:	3,90 [mm]	Density:	[kg/m ³]
Outer diameter:	[mm]	Remarks:	
Inner diameter:	[mm]		

Pre-conditioning:

	Conditions	Duration days
Client: (information supplied by client)	Normal 23/50-1 DIN 50014	
Test laboratory:	Standard 23/50-1 DIN 50014	13

Sample preparation:

Exposed surface: coated side

Test according to DIN 5510 Part 2 : 2009-05
 Preventive fire protection in railway vehicles - Part 2: Fire behaviour and fire side effects of materials and parts; Classification, requirements and test methods
 Determination of smoke toxicity in the smoke chamber according to ISO 5659-2

Test Report No.: 10621 / 36371

5. Test results:

5.1 Test conditions

FTIR Spectrometer		Gaset CR 4000 SN 122279			
FTIR gas cell		Gaset 5m multireflection			
Filter		M&C Products FT-F-2T-H2			
		M&C Products FT-F-2T-H2			
Irradiance	[kW/m ²]	25			
Test mode		flaming			
Sample		1	2	3	Avg.
Initial weight without Al sheet	[g]	33,9	32,7	33,8	33,5
Initial weight with Al sheet	[g]	34,8	33,6	34,9	34,4
Final weight with Al sheet	[g]	28,9	27,6	29,0	28,5
Mass loss	[g]	5,9	6,0	5,9	5,9
Chamber wall temperature at start of test	[°C]	40	44	46	43
Temperature at sampling point (4')	[°C]	58	62	64	61,6
Temperature at sampling point (8')	[°C]	60	63	65	62,8
Chamber pressure at 4'	[mmH ₂ O]	53	61	32	49
Chamber pressure at 8'	[mmH ₂ O]	53	52	29	45
Ignition after	[s]	20	24	22	22
Extinguishment	[s]	600	600	600	600
Ambient temperature	[°C]	23			
Ambient pressure	[bar]	0,990			

Test Report No.: 10621 / 36371

5.2 Gas concentrations and smoke gas toxicity

Sampling Time		Gas concentrations							
		4 minutes				8 minutes			
Sample #		1	2	3	Avg.	1	2	3	Avg.
CO ₂	[mg/m ³]	17.254	14.368	14.677	15.433	19.331	20.933	19.626	19.963
CO	[mg/m ³]	222	233	233	230	280	280	274	278
HF	[mg/m ³]	nd	nd	nd	nd	nd	nd	nd	nd
HCl	[mg/m ³]	nd	nd	nd	nd	nd	nd	nd	nd
HBr	[mg/m ³]	nd	nd	nd	nd	nd	nd	nd	nd
HCN	[mg/m ³]	nd	nd	nd	nd	nd	nd	nd	nd
NO	[mg/m ³]	41	38	40	40	48	47	46	47
NO ₂	[mg/m ³]	4	5	nd	*	nd	7	nd	*
SO ₂	[mg/m ³]	nd	nd	nd	nd	nd	nd	nd	nd
CIT		0,1782	0,1650	0,1637	0,1690	0,1952	0,2087	0,1927	0,1989

¹⁾ nd = below detection limits * Mean value statistically not sound

5.3 Calculation of allowable FED

$$FED(t_{zul}) = \frac{(CIT_4 + 0,5 \cdot CIT_8) \cdot 4 \text{ min} + CIT_8 \cdot (t_{zul} - 8 \text{ min})}{30 \text{ min}}$$

FED (15 min) =	$\frac{4 \cdot CIT_4 + 9 \cdot CIT_8}{30}$
FED (15, determined)	0,0822
FED (30 min) =	$\frac{4 \cdot CIT_4 + 24 \cdot CIT_8}{30}$
FED (30, determined)	0,1816

BASF – Fire Safety Technology

Test according to DIN 5510 Part 2 : 2009-05
Preventive fire protection in railway vehicles - Part 2: Fire behaviour and fire side effects of materials
and parts; Classification, requirements and test methods
Determination of smoke toxicity in the smoke chamber according to ISO 5659-2

Test Report No.: 10621 / 36371

Observations:

6. Test equipment:

Test apparatus	PE 0018
Calliper gauge	MB 0029
Balance	MW 0007
FTIR spectrometer	MI 0002

BASF – Fire Safety Technology

Test according to DIN 5510 Part 2 : 2009-05
 Preventive fire protection in railway vehicles - Part 2: Fire behaviour and fire side effects of materials and parts; Classification, requirements and test methods
 Determination of smoke toxicity in the smoke chamber according to ISO 5659-2

Test Report No.: 10621 / 36371

7. Requirements: $FED \leq 1$ at exposure times of 15 or 30 minutes

1	2	3	4	5
No.	Vehicle parts requiring certification	Fire protection level as specified in DIN 5510-1	Maximum allowable exposure time min	Remarks
1	Vehicle superstructure, including bottom floor, external vehicle cladding (roof, sides, face) but excluding driver's cab	1	—	
2		2 to 4	30	
3	External doors, face end doors, skirts, cladding and superstructure of driver's cab, fittings	1	—	
4		2 to 4	30	
5	Roof-mounted parts and roof edge fairing parts	2 to 4	30	
6	Underframe streamlining	1	—	
7		2 to 4	30	
8	External windows, frames without seals	1 to 3	—	
9		4	30	
10	External windows, pane and pane composites	1	—	
11		2 to 4	30	
12	Gangway between coaches	1	—	
13		2 to 4	30	
14	Cladding of gangway systems (rubber cylinders, bellows-type)	1	—	
15		2 to 4	15	
16	Ducts for heating, ventilation and cooling – built into roof section	1	—	
17		2 to 4	30	
18	Ducts for heating, ventilation and cooling – built into areas other than the roof section	1	—	
19		2 to 4	30	
20	Hoses for heating, ventilation and cooling	1	—	
21		2 to 4	15	
22	Conduits for electrical installations and electrical installation tubes – built into roof section	1	—	Conduits and tubing for electrical installations in engine spaces, switchgear cabinets and control boxes are exempted.
23		2 to 4	30	
24	Conduits for electrical installations and electrical installation tubes – built into areas other than the roof section	1	—	Conduits and tubing for electrical installations in engine spaces, switchgear cabinets and control boxes are exempted.
25		2 to 4	30	
26	Pipes and hoses for fuel, hydraulics, pneumatics, water and drainage	1	—	
27		2 to 4	15	

BASF – Fire Safety Technology

Test according to DIN 5510 Part 2 : 2009-05
Preventive fire protection in railway vehicles - Part 2: Fire behaviour and fire side effects of materials and parts; Classification, requirements and test methods
Determination of smoke toxicity in the smoke chamber according to ISO 5659-2

Test Report No.: 10621 / 36371

Requirements (2)

1	2	3	4	5
No.	Vehicle parts requiring certification	Fire protection level as specified in DIN 5510-1	Requirement: permitted exposure time min	Remarks
28	Insulating materials (sound-proofing and/or thermal insulation) for roofs, side panels and face ends, external doors and floors, applied to the internal surfaces of the vehicle	1	—	see nos. 30 and 31
29		3	—	
30	Insulating materials (sound-proofing and/or thermal insulation) for roofs, side panels and face ends, external doors and floors, applied to the internal surfaces of the vehicle – areas below bottom edge of windows	2 and 4	30	
31				
32	Underbody coating	1 to 4	—	
33	Insulating materials for roofs, side panels and face ends, external doors and floors (products in sheet or web form)	1	—	
34	Insulating materials for side and face end panels and floors in the – areas below the bottom edge of the windows as well as insulating material for external doors (products in sheet or web form)	2 to 4	30	
35	Insulating materials for roofs, side panels and face ends (products in sheet or web form) – areas above the bottom edge of the windows	2 and 4	—	S5 required
36		3	30	
37	Internal furnishings such as ceilings, ceiling recesses as well as hatches, boxes and hoods in the ceiling and ceiling recess area	1	—	
38		2 and 3	30	
39		4	—	S5 required
40	Cover strips, cover profiles in the ceiling and ceiling recess area	1	—	
41		2 and 3	30	
42		4	—	S5 required
43	Interior furnishings such as claddings of side and face panels, partition walls, partitions and covers, boxes, cabinets and hoods in this area; interior doors and interior cladding of the external doors.	1	—	
44		2 and 3	30	
45		4	30	
46	Cover strips, profiles and frames; mountings and covers for information and advertising panels, newspaper boxes; lockers and advertising boxes in the vehicle's interior	1	—	
47		2 and 3	30	
48		4	30	

BASF – Fire Safety Technology

Test according to DIN 5510 Part 2 : 2009-05
 Preventive fire protection in railway vehicles - Part 2: Fire behaviour and fire side effects of materials and parts; Classification, requirements and test methods
 Determination of smoke toxicity in the smoke chamber according to ISO 5659-2

Test Report No.: 10621 / 36371

Requirements (3):

1	2	3	4	5
No.	Vehicle parts requiring certification	Fire protection level as specified in DIN 5510-1	Requirement: permitted exposure time min	Remarks
49	Floors including steps (substrate and floor covering permanently joined)	1	—	
50		2 to 4	30	
51	Runners, carpets	1	—	
52		2	15	
53		3 and 4	30	
54	Covers for luminaires, including grilles	1	—	
55		2 and 3	30	
56		4	—	S5 required
57	Luggage racks	1	—	
58		2	30	
59		3	30	
60		4	—	S5 required
61	Window locking frame, if not included in no. 43	1	—	
62	Window locking frame, if not included in no. 44	2 and 3	30	
63	Window locking frame, if not included in no. 45	4	30	
64	Window framing	1	—	
65		2 to 4	15	
66	Curtains and roller blinds	1	—	
67		2 and 3	30	
68		4	30	
69	Tables, windowsill tables, folding tables	1	—	
70		2 and 3	30	
71		4	30	
72	Dynamically stressed seals for external and interior doors; seals for doors in the vehicle face ends	2 to 4	15	
73	Statically stressed seals for external and interior doors	2 to 4	15	
74	Seat	1	—	
75		2 to 4	30	Can also be evaluated in tests under real conditions
76	Folding seats without back rest (auxiliary seats), arm rests, head rests, side supports on headrests, pillows	1	—	If the material structure is identical to that of a tested seat (nos. 74 and 75) certification corresponding to this component is valid.
77		2 to 4	30	

BASF – Fire Safety Technology

Test according to DIN 5510 Part 2 : 2009-05
Preventive fire protection in railway vehicles - Part 2: Fire behaviour and fire side effects of materials and parts; Classification, requirements and test methods
Determination of smoke toxicity in the smoke chamber according to ISO 5659-2

Test Report No.: 10621 / 36371

Requirements (4):

1	2	3	4	5
No.	Vehicle parts requiring certification	Fire protection level as specified in DIN 5510-1	Requirement permitted exposure time min	Remarks
78	Covers and cladding parts of seats, seat shells, backrest shells, folding tables attached to passenger seats	1	—	
79		2 and 3	30	
80		4	30	
81	Hand-holds and hand rails	1 to 4	—	no SR requirements
82	Ashtrays, waste bins and bins for collecting recyclable materials	1 to 4	—	S5 required
83	Water containers to be installed in the vehicle interior excluding enclosed driver's cabs and engine compartments	2 to 4	30	
84	Galley components in the vicinity of the stove	1 to 4	—	S5 required
85	Other galley components	1 to 4	—	no SR requirements
86	Couchettes and beds (mattresses and/or upholstery combinations) without bed linen	1 to 4	30	Can also be evaluated in tests under real conditions
87	Interior furnishings such as walls, ceilings, doors, lids, washbasins, luminaire covers and mirrors in toilets and washrooms	1 to 3	30	
88		4	—	S5 required
89	Washbasins, toilet basins, soap dispensers, paper towel containers, containers for cleaning cloths and hygiene bags, cigarette rests in toilets and washrooms	1 to 4	—	S5 required
90	Toilet covers, toilet seats	1 to 4	30	
91	Floors in toilets and washrooms	1 to 4	30	
92	Interior furnishings of closed staff rooms, e.g. walls, ceilings, doors, lids, boxes, cabinets and driver's desks	1 to 4	—	no SR requirements
93	Floors in closed staff rooms	1 to 4	—	no smoke generation requirements
94	Seats for enclosed staff compartments	1 to 4	—	no smoke generation requirements

Requirements (5): Reference concentrations for toxic gases

Carbon dioxide	CO ₂	72.000	[mg/m ³]
Carbon monoxide	CO	1.380	[mg/m ³]
Hydrogen fluoride	HF	25	[mg/m ³]
Hydrogen chloride	HCl	75	[mg/m ³]
Hydrogen bromide	HBr	99	[mg/m ³]
Hydrogen cyanide	HCN	55	[mg/m ³]
Nitrogen dioxide	NO ₂	38	[mg/m ³]
Sulfur dioxide	SO ₂	262	[mg/m ³]